

Sub: Availability Of Manganese Ore for the quarter Jan-March 2025 Q4.

Certain quantities of Manganese ore are available for Direct Sale as per Annexure “A”.

The buyer(s) are requested to send their requirement of ore on customer portal (<https://moillimited.co.in/moilcrm>) and confirmation copy on email id: rppatil@moil.nic.in on or before **06.03.2025 by 05.15 PM** and may contact the undersigned for further details. Details of E-mail is as under:

E-mail id: rppatil@moil.nic.in

Mobile No:+91-9503135508

We would request that customers may kindly telephonically confirm with us receipt of requirement at our end after sending the same through email.

R.P.Patil
GM(Marketing)
MOIL LTD., Nagpur



MOIL LIMITED

(A GOVERNMENT OF INDIA ENTERPRISE)

ORE CODE, SPECIFICATIONS & AVAILABILITY AS ON 04.03.2025

ANNEXURE-A

Ore Code	Description	Mn%	Ph%	SiO2	Fe%	+75mm	+25mm	+10mm	+6mm	+3mm	-3mm	Available qty apprx (in MT)
FERRO												
BG4582	37% BALAGHAT FERRO GRADE LU	37	0.112	25	5.5			96	1.5	1.5	1	74
BG4583	37% BALAGHAT FERRO GRADE JIG	37	0.112	26	5.5			60	23	12.5	4.5	117
BL4528	3RD GR BED (N-16)	38	0.25	26	7	3	85	7	2	2	1	81
CH4551	CHIKLA FERRO GRADE (N-18)	35.5	0.275	26	7.5			93	3	1.5	2.5	2341
DB2268	3RD GR 42/44 'S' (N-03)	43	0.2	13	7.5			60	23	10	7	130
DB4538	4TH GR DB SMALL (N-17)	37	0.22	13	7.5			60	23	10	7	56
GM4187	3RD GR JIGGED (HAND SCRE	38	0.25	17.5	8.5			50	20	22	8	96
GM4417	4TH GR. LUMP (N-06)	32	0.25	28	7.8	6	60	32	1	1		181
GM4516	GM FERRO GARDE(Mn-37%)N-16	37	0.23	24	7		61	18	10	6	5	824
GM4552	GUMGAON FERRO GRADE (N-18)	33	0.25	25	7			52	23	18	7	393
KD1526	1ST GR. LUMP (N-16)	46	0.22	17	5.2	-	-	88	3	3	6	7322
KD3508	3RD GR. SMALL (N-14)	39	0.21	21	7			50	27	9	14	5501
KD4543	4TH GR LUMP (N-17)	34	0.25	28	6			94	2	2	2	1431
KD4565	34% MN ORE SMALL (N-19)	34	0.25	28	6				40	50	10	532
MS4525	MN 33% LUMP (N-16)	33	0.27	30	8			80	10	5	5	79
SP3515	SITAPATORE 36% FERRO GR. ORE	36	0.5	17	11			75	12	8	5	65
SP4454	LOW GRADE BED LUMP 38%	38	0.37	22	9	-	60	25	9	6	-	9002
TD4427	4TH GR. SMALL (N-06)	38	0.26	20	8			40	30	18	12	351
TD4505	FERRO GRADE SMALL (N-14)	34	0.31	23	9			50	30	12	8	200
UK4571	FERRO GRADE SMALL (MN33%) N	33	0.2	26.37	5.17			42	22	20	16	232
UK4581	37% UKWA FERRO GRADE LUMP (37	0.2	27	6			85	8	4	3	3048
TOTAL FERRO GRADE												32056
SILICO MANGANESE GRADE --LOW Mn(30%)												
SMGR LMP	SMGR LMP	30	5/0.32	29/33	7/9	-	90/95	1	1	1	2	200
SMGR SMH	SMGR SMH	30	5/0.32	29/33	7/9			80	10	3	7	145
CHS578	CH SMGR 30% SMALL(N-23)	30	0.3	30	7.5	-	-	6	60	20	14	4798
TOTAL SILICO MANGANESE GRADE--LOW Mn(30%)												5143
SILICO MANGANESE GRADE--LOW Mn(25%)												
BLL492	SM GRADE 25% (N-11)	25	0.25	42	7	-	-	97	1	1	1	132
CHL442	CHIKLA LOW GRADE SMALL	25	0.275	37	7			93	3	2	2	8000
DBL456	25 % S.M. GR. LUMP	25	0.2	35	9	5	85	3	3	2	2	4840
DBL457	25 % S.M. GR. SMALL	25	0.2	35	9		5	70	9	8	8	2306
DBL572	DB SMGR (25%) SMALL (N-21)	25	0.19	30	11				35	25	40	200
GML464	SM GRADE 25%	25	0.28	36	8.5			50	20	22	8	8000
KDL446	25% SM GR KANDRI (N-06)	25	0.27	35	6	3	90	4	1	1	1	96
MSL498	SM Grade 25% Mn (N-12)	25	0.3	40	8	-	-	70	16	6	8	80
TDL499	SM Grade Small 25% Mn (N-12)	25	0.35	45	7.5	-	-	90	5	2	3	8000
SPL463	25 % S.M. GRADE	25	0.4	38	9	3	90	-	-	4	3	261
TOTAL SILICO MANGANESE GRADE--LOW Mn (25%)												31915
FINES												
BGF452	BG HUTCH PRODUCT (N-06)	30	0.1	30	6.5				3	17	80	649
BGF534	BG FINES (N-17)	27	0.2	35	6.5				3	17	80	1830
CHF473	CHIKLA FINES (N-09)	26	0.22	35	6				6	27	67	1721
DBF487	DONGRI BUZ FINES (N-10)	28	0.2	26	12					5	95	5304
GMF569	GUMGAON FINES	26	0.2	36	6.5					25	75	406
KDF576	KANDRI FINES 26% (N-22)	26	0.23	36	6					10	90	800
TOTAL FINES												10710
CHEMICAL GRADE												
DB2320	DONGRI BUZ. 42/44(-10)MM	43	0.26	13	8.5				25	30	45	216
DB3385	DONGRI 38/40% CHEM(-10)	39	0.2	18	10				25	30	45	126
TOTAL CHEMICAL												342
GRAND TOTAL												80166